Smart Link Better Life.

62.5/125μm Multimode Fibre

Yangtze Optical Fibre and Cable Joint Stock Limited Company

YOFC 62.5/125μm Multimode Fibre complies with or exceeds ISO/IEC 11801 OM1 specification, IEC 60793-2-10 type A1b Optical Fibre Specification, and TIA/EIA-492AAAA-A detail specification.

Features	Benefits and Applications
• Extremely refined refractive index profile • Low attenuation • High bandwidth at both 850nm and 1300nm wavelengths • Superior geometry, uniformity	• Local area networks (LAN) • Video, voice and data services • Gigabit Ethernet (IEEE 802.3z) using laser or light emitting diode (LED) sources
• Coated with YOFC's proprietary dual layer UV curable acrylate	• Optimized performance in tight-buffer cable applications • High resistance to micro-bending • Stable performance over a wide range of environmental conditions

/ Tel: 400-006-6869
/ E-mail: 400@yofc.com
/ Web: www.yofc.com

Characteristics	Conditions	Specified values	Units
Geometry Characteristics			
Core Diameter	–	62.5±2.5	[μm]
Core Non-Circularity	–	≤5.0	[%]
Cladding Diameter	–	125.0±1.0	[μm]
Cladding Non-Circularity	–	≤1.0	[%]
Coating Diameter	–	245±7	[μm]
Coating/Cladding Concentricity Error	–	≤10.0	[μm]
Coating Non-Circularity	–	≤6.0	[%]
Core/Cladding Concentricity Error	–	≤1.5	[μm]
Delivery Length	–	up to 17.6	[km/reel]
Optical Characteristics			
Attenuation	850nm	≤2.7	[dB/km]
	1300nm	≤0.6	[dB/km]
Overfilled Modal Bandwidth	850nm	≥200	[MHz·km]
	1300nm	≥500	[MHz·km]
Numerical Aperture	–	0.275±0.015	--
Group Refractive Index	850nm	1.496	--
	1300nm	1.491	--
Zero Dispersion Wavelength, λ_0	–	1320~1365	[nm]
Zero Dispersion Slope, S_0	1320nm≤λ_0≤1348nm	≤0.11	[ps/(nm²·km)]
	1348nm≤λ_0≤1365nm	≤0.001 (1458-λ_0)	[ps/(nm²·km)]
Macrobending Loss	–	--	--
100 Turns @ 37.5 mm Radius	850nm	≤0.50	[dB]
	1300nm	≤0.50	[dB]
Backscatter Characteristics	**1300nm**		
Step (Mean of Bidirectional Measurement)	–	≤0.10	[dB]
Irregularities Over Fibre Length and Point Discontinuity	–	≤0.10	[dB]
Attenuation Uniformity	–	≤0.10	[dB/km]
Environmental Characteristics	**850nm & 1300nm**		
Temperature Cycling	-60°C to 85°C	≤0.10	[dB/km]
Temperature-Humidity Cycling	-10°C to 85°C, 4% to 98% RH	≤0.10	[dB/km]
Water Immersion	23°C, 30 days	≤0.10	[dB/km]
Dry Heat	85°C, 30 days	≤0.10	[dB/km]
Damp Heat	85°C, 85% RH, 30 days	≤0.10	[dB/km]
Mechanical Specification			
Proof Test	–	≥9.0	[N]
	–	≥1.0	[%]
	–	≥100	[kpsi]
Coating Strip Force	typical average force	1.5	[N]
	peak force	≥1.3, ≤8.9	[N]
Dynamic Stress Corrosion Susceptibility Parameter (n_d, typical)	–	20	--